



BDW Marine LLP
Units 1 & 2 Poplars Farm
Aythorpe Roding
Dunmow
Essex CM16 1RY

Tel: 01884 220016
Fax: 0845 280 2195
Email: enquiries@Premier-Paints.co.uk

TECHNICAL DATA SHEET

PREMIER HULL & TOPSIDE UNDERCOAT - REF: - 52L643

A quality tough durable undercoat that provides a perfect smooth and sandable base to maximise the performance and finish to high gloss and semi-gloss products in industrial/commercial marine environments.

| | |
|-----------------------------------|--------------------------|
| PACKAGE SIZE | 1 Litre. |
| COLOUR | BS 4800, BS 381C, R.A.L. |
| FLASH POINT | Above 32°C |
| DRYING TIME @ 20°C | Surface Dry: 2 - 4 hrs |
| VOLUME SOLIDS | 50% (+/- 2%) |
| RECOMMENDED W.F.T. | 60 microns |
| RECOMMENDED D.F.T. | 30 microns |
| THEORETICAL SPREADING RATE | 16 Sq. Metres/Litre |
| THINNERS | No. 2 |
| SHELF LIFE | 12 mths |
| V.O.C. | 340 g/litre |

SURFACE PREPERATION

Ensure surface is free from rust, moisture, oil or other surface contamination.

APPLICATION

| | |
|---------------------------|---|
| AIRLESS SPRAY | Nozzle Size 13 thou, Fan Angle - 80°, Tip Pressure 2000 p.s.i. |
| CONVENTIONAL SPRAY | Nozzle Size 50 thou, Atomising Pressure 50 p.s.i., Fluid Pressure 10 p.s.i. |

BRUSH OR ROLLED Do not apply too thickly as this may impair through drying.



BDW Marine LLP
Units 1 & 2 Poplars Farm
Aythorpe Roding
Dunmow
Essex CM16 1RY

Tel: 01884 220016
Fax: 0845 280 2195
Email: enquiries@Premier-Paints.co.uk

HEALTH & SAFETY

Refer to M.S.D.S. prior to use.

Provide adequate ventilation. Prolonged skin contact inhalation of vapour must be avoided. Eye contamination - Flush with eyewash or warm water for 10 mins. Clean hands after use.

Any person or company using this product without first making enquiries as to the suitability for the intended purpose does so at their own risk, and BDW Marine LLP can accept no liability for the performance of the product or for any loss or damage arising out of such use.